



## CAST DATA SHEET HX30890M

Cast multilayered high performance vinyl, 110 microns, coated with a solventbased pressure sensitive acrylic adhesive. For easier application the thickness of the film has been increased. Structured adhesive for faster application and convenient air egress. Specially designed for full vehicle wraps and marking applications on vehicles with complex compound curves. Black matt finish.

### **SPECIFICATIONS:**

	<u>Average values</u>	<u>Standard</u>
• Thickness (µm):	110	
• Tensile strength (N/25mm):	min. 30	HEXNFX41021
• Elongation at break (%):	min. 150	HEXNFX41021
• Dimensional stability (mm): after 168h at 70°C	< 0.4	HEXRET001

### **LINER:**

- Embossed PE coated paper liner 145g/m<sup>2</sup> grey imprint “THE CAST by HEXIS”.
- Stable under hygrometric variations.

### **ADHESIVE PROPERTIES:**

- |  |      |           |
|--|------|-----------|
| • Peel on glass at 180° (N/25mm):  |      | HEXFTM001 |
| 20 minutes after application   | 18   |           |
| 24 hours after application   | 18   |           |
| • Initial tack (N/25mm):   | 20   | HEXFTM009 |
| • Release (N/25mm):  | 0.20 | HEXFTM003 |
| • The adhesive is resistant to most chemicals (alcohol, diluted acids, oils and hydrocarbons). |      |           |

**RECOMMENDATIONS:**

- Recommended minimum application temperature: +15 °C (59 °F). Apply preferably between 20 °C and 25 °C (68 °F and 77 °F).
- Optimum environment -40 °C to +90 °C (-40 °F to +194 °F).
- Highly conformable, recommended for vehicles.
- For further information about the application of the CAST HX20000-HX30000 film please refer to Professionals/Data Sheets on our website, available soon.
- The colour of the films is controlled by Hexis in order to ensure faithful reproduction of colour tints. Nevertheless, in the case of installs that require the use of several rolls of the same colour, Hexis recommends to use only one lot number of this colour.
- The HX30890M is a fragile product and is easily scratched or marked. Handle with care.

**ADHESIVE:**

- Acrylic solvent based.
- Immediate and permanent adhesion; maximum adhesion after 24 hours.
- Structured adhesive for convenient application and elimination of air bubbles.
- Dry application.

**SHELF LIFE:**

- 2 years at +15 °C to +25 °C (+59 °F to +77 °F) and 30 to 70 % relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

**DURABILITY:**

- The pigments (colouring) of the PVC influence the durability of the colours. The durability is confirmed by aging tests of the CAST under UV rays and by natural exposure: the durability given below is the moment when a gradual decline or modification of the appearance shows.

Colour	Nordic climate Central Europe	Mediterranean climate	Tropical and marine climate	Desert climate
Black matt	10 years	8 years	7 years	6 years

These results are obtained under vertical outdoor exposure and the conditions of the indicated durability depend on this position up to a few degrees. Other positions accentuate the climatic influences and alterations of gloss, colour or even a slight powder effect may appear.

**Note:**

If in doubt about the compatibility of the product with any particular application we recommend that the user carry out a trial before the final application or seek advice from the manufacturer. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force. All data are believed to be correct but do not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The buyer has to determine the suitability of the materials for the intended purpose prior to purchase. HEXIS S.A. or its affiliates assume no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: [www.hexisgroup.com](http://www.hexisgroup.com).